

FryeFlow Systems™

“The Ultimate Concrete Washout Pit or Pumping Water Silt Separator”



**5,000 lb strap
lifting capacity**

The reusable FryeFlow Concrete Washout Pit allows developers and builders the opportunity to set budgets and control cost.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Wide Width Tensile Strength	ASTM D 4595	kN/m (lbs/ft)	43.8 (3000)	40.3 (2760)
Grab Tensile Strength	ASTM D 4632	kN (lbs)	1.76 (400)	1.40 (315)
Grab Tensile Elongation	ASTM D 4632	%	15	15
Trapezoid Tear Strength	ASTM D 4533	kN (lbs)	0.67 (150)	0.73 (165)
Mullen Burst Strength	ASTM D 3786	kPa (psi)	5506 (800)	
Puncture Strength	ASTM D 4833	kN (lbs)	0.67 (150)	
Apparent Opening Size (AOS)	ASTM D 4751	mm (U.S. Sieve)	0.425 (40)	
Permittivity	ASTM D 4491	sec ⁻¹	0.90	
Permeability	ASTM D 4491	cm/sec	0.066	
Flow Rate	ASTM D 4491	l/min/m ²	2851	
UV Resistance (at 500 hours)	ASTM D 4355	(gal/min/ft ²) % strength retained	(70) 90	

Physical Properties	Test Method	Unit	Typical Value
Mass/Unit Area	ASTM D 5261	g/m ² (oz/yd ²)	271 (8.0)
Thickness	ASTM D 5199	mm (milis)	0.89 (35)
Roll Dimensions (width x length)	--	m (ft)	4.5 (15) x 91 (300)
Roll Area	--	m ² (yd ²)	418 (500)
Estimated Roll Weight	--	kg (lbs)	120 (265)



Maintenance on FryeFlow Systems™ is easy.

- Woven Geotextile for strength
- Installs in minutes
- Re-usable
- A one time expense frame
- Replacement Bags available
- Sizes available to accommodate different sizes of machinery for disposal purposes

P.O. Box 622 • Granville, Ohio 43023

Phone • 740-788-9150

Fax • 740-788-9185

Email • mike@fryeflowsystems.com

For more information go to our website at
www.fryeflowsystems.com

